

## Product Data Sheet:

SWIMMING POOL PAINT/  
CHLORINATED RUBBER  
WATERPROOFING PAINT

5L



AVAILABLE COLOURS

**A FLEXIBLE, HARD WEARING, LONG LASTING CHLORINATED RUBBER WATERPROOFING PAINT THAT COMBINES EXCELLENT CHEMICAL AND WATER RESISTANCE WITH A DECORATIVE MID SHEEN FINISH.**

FixMaster Swimming Pool paint is an elastomeric waterproof paint which is ideal for application on any internal or external surface that requires excellent water resistance. Can be used as a base coat on pools or on top of previously painted surfaces.

- Suitable for long term immersion in water
- Excellent resistance to severe pollution and chemical damage
- Suitable for internal and external areas
- Durable and easy to apply

### Surface Preparation

Concrete surfaces to be coated should be at least 4 weeks old, have a moisture content of less than 7% and be free from contaminants or surface laitance. Traces of grease or oil can be removed using a degreaser. Very smooth concrete or surface laitance should be treated with an acid etch cleaner to ensure good adhesion. Treated areas should be thoroughly washed down and allowed to dry. It is advisable to coat a small test area to test compatibility with previous coatings. If the test is successful, previously painted surfaces should be abraded to improve adhesion and remove any loose or weak material. All cracks, voids or holes should be filled with a cement based filler, which should now be treated as new concrete and spot primed. Wash with a detergent solution to remove any contamination including body fats which collect at the waterline. Finally, wash with fresh water and allow to dry completely before painting.

### Mixing

Mix thoroughly for approximately 5 minutes using a wide bladed stirrer.

### Application

Best results are obtained in warm (minimum 15°C), dry conditions. Avoid application of coating in very hot, direct sunlight as this may lead to blistering. Apply using a brush or short pile roller. On bare concrete dilute the first coat with approximately 10-20% thinners by volume prior to application. This will act as a binding primer. Once dried, apply a second coat at full strength. On previously painted surfaces it is recommended to apply 2 thin coats rather than one thick coat, this will prolong the life and performance of the coating. Always leave the paint for a minimum of three days after application of the final coat before filling the pool with water. In temperatures below 10°C, this should be

### CURING TIMES @ 20°C:

Touch Dry	30 minutes
Hard Dry	90 minutes
Overcoat	3 Hours

### COVERAGE:

5L will cover approximately 30-40m<sup>2</sup>. Coverage will be reduced on porous or open textured surfaces.

### SHELF LIFE:

Two years in sealed containers. Store in a cool dry and well-ventilated place. (5-30°C)

### CLEANING TOOLS:

Use thinners to clean tools.

### SAFETY:

Refer to the Material Safety Data Sheet for information on correct handling and application of the product.